



Bubble formation in melts with basalt-like composition

Keding, Ralf; Jensen, Martin; Yue, Yuanzheng

Publication date:
2010

Document Version
Early version, also known as pre-print

[Link to publication from Aalborg University](#)

Citation for published version (APA):
Keding, R., Jensen, M., & Yue, Y. (2010). *Bubble formation in melts with basalt-like composition*. Abstract from 10th ESG Glass Conference, Magdeburg, Germany.

General rights

Copyright and moral rights for the publications made accessible in the public portal are retained by the authors and/or other copyright owners and it is a condition of accessing publications that users recognise and abide by the legal requirements associated with these rights.

- Users may download and print one copy of any publication from the public portal for the purpose of private study or research.
- You may not further distribute the material or use it for any profit-making activity or commercial gain
- You may freely distribute the URL identifying the publication in the public portal -

Take down policy

If you believe that this document breaches copyright please contact us at vbn@aub.aau.dk providing details, and we will remove access to the work immediately and investigate your claim.

Bubble formation in melts with basalt-like composition

Ralf Keding, Martin Jensen, Yuanzheng Yue

Section of Chemistry, Aalborg University, 9000 Aalborg, Denmark

yy@bio.aau.dk

The homogeneity of glasses is an important quality parameter and therefore of major importance to glass melting technology. Beside inhomogeneities such as striae, bubbles reduce the quality of melts due to the highly different mechanical and optical properties between melt and gas. In this work, basaltic melts produced in a cupola furnace and cooled to T_g within 10s are used for inspection of bubbles. This inhomogeneous, striated glass contains 0.32 Vol% bubbles with a bimodal size distribution. The smaller bubbles with an average diameter of approx. 4 μm contribute to 0.07 vol% to the glass while bubbles with a diameter larger than 20 μm contribute to 0.25 vol% to the glass. The bubble volume distribution indicates that the bubbles are created through at least 2 mechanisms. As large numbers of smaller bubbles are present, the bubble nucleation mechanism must be highly efficient. Detailed microscopic investigations of the size and location of small bubbles show, that they are randomly distributed. In the striated glass, the bubble occurrence is independent of the striae.